



(11) Publication number : **0 668 083 A1**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number : **95101228.5**

(51) Int. Cl.⁶ : **A61L 31/00, A61L 17/00,
A61L 27/00, A61L 15/26**

(22) Date of filing : **30.01.95**

(30) Priority : **10.02.94 US 194766**

(43) Date of publication of application :
23.08.95 Bulletin 95/34

(84) Designated Contracting States :
DE FR GB IT

(71) Applicant : **United States Surgical Corporation**
150 Glover Avenue
Norwalk, Connecticut 06856 (US)


(72) Inventor : **Liu, Cheng-Kung**
2 Minerva Street
Norwalk, CT 06851 (US)

Inventor : **Jiang, Ying**
34 Grandview Terrace
North Haven, CT 06473 (US)
Inventor : **Roby, Mark S.**
11 Grace Lane
Killingworth, CT 06419 (US)
Inventor : **Bennett, Steven L.**
2 Darling Street, Unit 2E
Southington, CT 06489 (US)
Inventor : **Stevenson, Richard P.**
101 Pine Brook Road
Colchester, CT 06415 (US)
Inventor : **Pietrangeli, Jeffrey P.**
29 Martha Place
Bridgeport, CT 06606 (US)

(74) Representative : **Marsh, Roy David et al**
Hoffmann Eitle & Partner
Patent- und Rechtsanwälte
Arabellastrasse 4
D-81925 München (DE)

(54) **Composite bioabsorbable materials and surgical articles made therefrom.**

(57) The present invention relates to composite materials having a core portion 25 formed from a first bioabsorbable material and at least one shell portion 35, 38 of a second bioabsorbable material joined to the core portion. The first and second bioabsorbable materials have different rates of bioabsorption. In a preferred embodiment, the core portion is coextruded with the shell portion to form a composite filament or sheet. The materials of the present invention may be used as sutures or formed into medical devices or surgical articles for implantation within a living organism.



EP 0 668 083 A1

BACKGROUND OF THE INVENTION**1. Field of the Invention**

5 The invention relates to bioabsorbable materials and, more particularly, to composite bioabsorbable materials such as filaments and sheets. The composite includes a core of a first bioabsorbable material and at least one shell joined to the core, the shell being formed of a second bioabsorbable material. The first and second bioabsorbable materials preferably have different absorption rates.

2. Description of the Related Art

Bioabsorbable materials are known in the art for a variety of uses, particularly those uses in which the bioabsorbable material is implanted within a living organism for medical purposes. The term "bioabsorbable" is used to describe a material capable of being broken down into smaller constituents which can be metabolized and/or excreted by a living organism. Hydrolysis is one mechanism by which many bioabsorbable materials are broken down following implantation within a living organism. Such materials are useful for temporarily holding tissues in a desired position during healing, and being absorbed by the organism after a period of time.

Various bioabsorbable materials and medical devices made therefrom are known in the art. See, e.g., U.S. Patent Nos. 2,668,162; 2,703,316; 2,758,987; 3,225,766; 3,297,033; 3,422,181; 3,531,561; 3,565,077; 3,565,869; 3,620,218; 3,626,948; 3,636,956; 3,736,646; 3,772,420; 3,773,919; 3,792,010; 3,797,499; 3,839,297; 3,867,190; 3,878,284; 3,982,543; 4,047,533; 4,052,988; 4,060,089; 4,137,921; 4,157,437; 4,234,775; 4,237,920; 4,300,565; 4,429,080; 4,441,496; 4,523,591; 4,546,152; 4,559,945; 4,643,191; 4,646,741; 4,653,497; and, 4,741,337; U.K. Patent No. 779,291; D.K. Gilding et al., "Biodegradable polymers for use in surgery -- polyglycolide/poly(lactic acid) homo- and copolymers: 1", *Polymer*, Volume 20, pages 1459-1464 (1979), and D.F. Williams (ed.), *Biocompatibility of Clinical Implant Materials*, Vol. II, ch. 9: "Biodegradable Polymers" (1981).

Fiber-reinforced compositions used for surgical implants have been described in U.S. Patent Nos. 4,279,249; 4,550,449; 4,539,931; 4,743,257; 5,080,665. The fiber-reinforcements in these compositions provide increased strength and rigidity as may be required for bone repair, but render these compositions unsuitable where flexibility is required.

The present invention provides an implantable composite having a bioabsorption rate which varies over time and which is suitable for use in making a variety of medical devices, including those in which flexibility is a desirable characteristic.

SUMMARY OF THE INVENTION

The present invention relates to composite materials having a core portion formed from a first bioabsorbable material and at least one shell portion formed from a second bioabsorbable material joined to the core portion. The first and second bioabsorbable materials have different rates of bioabsorption. In a preferred embodiment, the core portion is coextruded with the shell portion to form a composite filament or sheet. The materials of the present invention may be used as sutures or formed into medical devices or surgical articles for implantation within a living organism.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1A illustrates a filament having a core portion and a shell portion according to the present invention. Fig. 1B illustrates a filament having a core portion and plural shell portions according to the present invention. Fig. 2A illustrates a sheet having a core portion and a shell portion according to the present invention. Fig. 2B illustrates a sheet having a core portion and plural shell portions according to the present invention. Fig. 3 is a coextrusion die optionally used to form a composite filament according to the present invention. Fig. 4 is a coextrusion die optionally used to form a composite sheet according to the present invention. Fig. 5 schematically illustrates a spinning process used to form filaments according to the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Referring now in detail to the drawings, Fig. 1A shows a filament 10 having a core portion 20 surrounded

by a shell portion 30. Shell portion 30 is joined to core portion 20 in such a manner that the two portions form a single structural element, i.e., filament 10. As such, filament 10 is a composite material in which all of the constituent elements contribute to the properties of the overall structure. Thus, filament 10 differs from coated filaments in that the coatings of such filaments, even for very thick coatings, do not contribute substantially to the strength of the filament.

Fig. 1B illustrates a composite filament 15 having a core portion 25, a first shell portion 35, and a second shell portion 38. In this embodiment, three separate materials may be used to form portions 25, 35, and 38 or the outer shell 38 may be the same material as the core portion 25. It is within the scope of the invention to produce filaments having any number of shell portions, depending upon the desired application of the filament.

Fig. 2A shows a composite sheet 40 having a core portion 50 and a shell portion 60. As with the composite filament of Fig. 1, the composite sheet 40 is fabricated so that the core 50 is joined to shell 60 such that the sheet behaves as a unified structural entity.

Fig. 2B shows a composite sheet 45 having a core portion 55 and shell portions 65 and 75. As with the composite filament of Fig. 1B, the sheet of Fig. 2B may include any number of shell portions, depending upon its ultimate use.

The dimensions of the core portion and shell portion can vary widely depending on a number of factors including the materials from which the composite is made and the intended use of the composite. Generally, the thickness of the core portion can range from about 0.001 mm to 10 mm or more, and the thickness of the shell portion can range from about 0.0001 mm to about 10 mm or more. For example, when the intended use is as a suture, a composite having a generally cylindrical core portion made from polydioxanone with a diameter in the range of about 0.01 mm to about 0.8 mm, with a shell portion made from polycaprolactone having a thickness of about 0.001 mm to about 0.5 mm will provide a filament having acceptable flexibility and strength. Where a more rigid, rod-like structure is desired, for example to be used as an osteosynthesis device, a generally cylindrical core portion made from polyglycolide with a diameter in the range of about 0.1 mm to about 1.0 mm with a shell portion made from polydioxanone and having a thickness of about 0.001 mm to about 0.2 mm will provide suitable rigidity and strength. For laminated sheet-like composites, useful for example as an adhesion barrier, hernia repair device, organ support, artificial skin substrate, bone plate, or stent, a core portion made from polyglycolide having a thickness of about 0.0 mm to about 5 mm having a shell portion made from polydioxanone and having a thickness of about 0.01 mm to about 0.25 mm joined to at least one side of the core portion would provide a composite with suitable physical characteristics.

In particularly useful embodiments, the core portion and shell portion are substantially co-extensive. It is also contemplated, however, that composites wherein the shell portion only partially covers the core portion can be made in accordance with this invention.

In a preferred embodiment, the materials used to form the core and shell portions of composite filament 10 and composite sheet 40 are bioabsorbable materials. Bioabsorbable materials used to form the core portions of these composites include, but are not limited to absorbable polymers made from glycolide, glycolic acid, lactide, lactic acid, caprolactone, dioxanone, trimethylene carbonate and dimethyl trimethylene carbonate. Copolymers (block or random) and mixtures and blends of such polymers or copolymers are also useful. Particularly useful absorbable polymers for the core portion include glycolide/lactide copolymers, polycaprolactone and polydioxanone.

Bioabsorbable materials used to form the shell portions of the composite filaments and sheets include, but are not limited to, absorbable polymers made from glycolide, glycolic acid, lactide, lactic acid, caprolactone, dioxanone, trimethylene carbonate and dimethyl trimethylene carbonate. Copolymers, (block or random) and mixtures and blends of such polymers and/or copolymers are also useful. Particularly useful polymers for the shell portion include polydioxanone, polycaprolactone, polylactide and polytrimethylene carbonate.

In one preferred embodiment of the present invention, the material used to form the core portion of the composite material has a higher rate of bioabsorption than the material used to form the shell portion of the composite material. This embodiment provides a strong, fiber-forming core material combined with a flexible shell material to provide a strong and flexible composite. Such core materials include, but are not limited to, bioabsorbable polymers, copolymers, or mixtures fabricated from glycolide or glycolic acid. Particularly preferred glycolide-containing polymers include copolymers of glycolide and lactide having 90% glycolide and 10% lactide, copolymers of glycolide and lactide having 92.5% glycolide and 7.5% lactide, and copolymers of glycolide and lactide having 18% glycolide and 82% lactide.

Materials having a lower rate of hydrolysis relative to the above glycolide-containing polymers are used to form the shell portion of the above composite material. Such relatively low rate hydrolysis rate materials include bioabsorbable polymers, copolymers, or mixtures fabricated from polydioxanone, polylactide, polycaprolactone, and polytrimethylene carbonate.

Particularly preferred combinations for composite materials having a core with a higher rate of hydrolysis

than the shell include, but are not limited to: a core of a copolymer of 18% glycolide and 82% lactide with a shell of polydioxanone; a core of a copolymer of 92.5% glycolide and 7.5% lactide with a shell of polydioxanone; a core of a copolymer of 25% glycolide and 75% lactide backfilled with glycolide as shown in U.S. Patent No. 4,844,854 with a shell of polydioxanone; a core of a triblock copolymer glycolide and dioxanone (as described above) with a shell of polycaprolactone; and a core of polydioxanone with a shell of polycaprolactone.

In another preferred embodiment of the present invention the material used to form the core portion of the composite material has a lower rate of bioabsorption than the material used to form the shell portion of the composite material. A higher rate of bioabsorption for the shell may, in some applications, serve to enhance tissue ingrowth and subsequent healing and wound closure. In this embodiment, the core may be of bioabsorbable polymers, copolymers, or mixtures fabricated from polydioxanone, polycaprolactone, and polytrimethylene carbonate. The shell may be of bioabsorbable polymers, copolymers, or mixtures fabricated from glycolide or glycolic acid. Particularly preferred glycolide-containing polymers include copolymers of glycolide and lactide having 90% glycolide and 10% lactide, copolymers of glycolide and lactide having 92.5% glycolide and 7.5% lactide, and copolymers of glycolide and lactide having 18% glycolide and 82% lactide.

The invention also contemplates using materials that are formed from the same composition for both the core and the shell portions. However, the morphology of the material of the core layer is selected to be different from the morphology of the material of the shell layer such that the two layers have different rates of bioabsorption. In general, it is known that amorphous polymers have higher rates of hydrolysis than crystalline versions of the same polymer. For example, the core material may be formed from an amorphous glycolide-containing polymer while the shell may be formed from a crystalline glycolide-containing polymer. Materials may be added to the polymer melt during formation of the composite material to promote crystallinity in the shell layer.

Although the above descriptions of preferred embodiments focus on bioabsorbable polymers, it is understood that those of skill may select any two bioabsorbable materials having different rates of bioabsorption to construct a bioabsorbable composite having the desired strength and bioabsorption characteristics needed for a particular medical or surgical application. Such bioabsorbable materials include, but are not limited to, collagen, chitin, chitin derivatives (e.g., chitosan), amino acid polymers (e.g., gelatin), and polysaccharides (e.g., dextran).

In another aspect of the present invention, composite materials having a core/shell structure may be fabricated using non-absorbable, biocompatible materials. Such materials include biocompatible polymeric materials which may be used in applications requiring a more permanent implantation of a prosthetic device. Core and shell polymeric materials include polyesters (e.g., polyalkyl terephthalates), polyamides (e.g., nylon), polyurethanes, polycarbonates, polyimides, fluoropolymers, polyolefins, vinyl polymers, etc.

Particularly preferred combinations include coextruded polyester and polyurethane fibers and coextruded low order and high order nylons such as nylon 6 or nylon 66 with nylon 12. Biocompatible implants such as sutures, soft tissue patches, surgical mesh, wound dressings, surgical felts, vascular grafts, nerve repair devices, artificial skin and sternum tape may be fabricated from the composite biocompatible materials.

The composite filaments and sheets of the present invention may be fabricated by a number of known polymer processing techniques. One preferred technique is coextrusion. Extrusion is a polymer processing technique in which a viscous melt is fed, under pressure, through a die in a continuous stream. In coextrusion, plural polymer melt streams feed through individual flow channels to be shaped as a single polymeric article. The polymer melts may be combined in several ways. Plural melts may be extruded separately from a single die, plural melts may be extruded partly separately followed by combined extrusion, or plural melts may be coextruded together.

A coextrusion die which may be used to form a composite filament according to the present invention is illustrated schematically in Fig. 3. In Fig. 3, the polymer melt used to form core 20 of filament 10 passes through central flow channel 70 where it is shaped as it passes through channel exit 72. The polymer melt used to form the shell 30 of filament 10 passes through outer flow channel 80 where it is shaped as it passes through channel exit 82. The two concentric polymer melts are joined at die exit 90, forming a continuous polymer melt.

A coextrusion die which may be used to form a composite sheet according to the present invention is schematically depicted in Fig. 4. In Fig. 4, the polymer used to form core portion 50 of sheet 40 is fed from an extruder to flow channel 100. The polymer used to form shell portion 60 of sheet 40 is fed from extruders to flow channels 110 and 120. The melts are in region 130 of the die and are formed into a sheet in region 140.

The dies and methods described above with reference to Figs. 3 and 4 are exemplary of coextrusion techniques used to form the filaments and sheets of the present invention. Any coextrusion process may be used to form the bioabsorbable composite filaments and sheets. Examples of other coextrusion processes suitable for use in forming the materials of the invention as well as examples of suitable extrusion apparatus which may be used with the dies of Figs. 3 and 4 are found in Vols. 4 and 6 of the Encyclopedia of Polymer Science

and Engineering, (John Wiley & Sons, New York), c. 1986, pp. 812-832 and 571-631, respectively, which are incorporated by reference herein.

In another preferred embodiment of the present invention, the composite materials may be spun into fibers to be used as monofilament or multifilament sutures. An exemplary spinning process is schematically illustrated in Fig. 5. To produce fibers having the core/shell structure of Fig. 1, the core and shell constituent materials are separately melted. The constituent materials are separately fed as polymer melts 213 to spinneret 215 and are combined in the manner shown in Fig. 3 just before the spinneret exit orifice. Although a single filament is shown for clarity in Fig. 5, it is understood that spinnerets having any desired number of exit orifices in a range of exit diameters may be used.

Molten monofilament 216 exits spinneret 215, passes through air gap 214, and enters quench bath 217. Air gap 214 is the distance between the spinneret exit and bath 217. Preferably, the air gap distance ranges from 0.5 to 100 centimeters and, more preferably, from about 1 to 20 centimeters. As monofilament 216 passes through bath 217, it solidifies. In a preferred embodiment, quench bath 217 is a water bath.

Within the quench bath, filament 216 is driven by drive roller 218. As it emerges from the bath, a wiper may optionally remove excess water. Monofilament 216 wraps around a first godet 221 and is prevented from slipping by nip roll 222. Godets 301, 302, 303, and 304 engage and drive the filament prior to a stretching operation. The number of godets is not critical; any suitable godet system may be employed in the spinning process of the present invention.

During stretching, monofilament 216 is drawn through hot water bath 223 by godets 224, 305, 306, 307, and 308 or any other suitable arrangement. This second godet system rotates at a higher speed than that of godet 104 to provide a desired stretch ratio.

Following stretching, monofilament 216 may be annealed within hot air oven chamber 225, driven by godets 226, 309, 310, 311, or 312, or any other suitable drawing system. Take-up reel 313 winds the finished monofilament product.

Other suitable fiber manufacture processes, including other spinning processes, which may be used to form the composite materials of the present invention are described in Volume 6 of the Encyclopedia of Polymer Science and Engineering, (John Wiley & Sons, New York), c. 1986, pp. 802-839, the disclosure of which is incorporated by reference herein.

Other polymer processing techniques may be used to form the composite filaments and sheets of the present invention. These include, but are not limited to, casting, injection molding, and blow molding. In short, any polymer processing technique capable of creating composite materials having shell portions adequately joined with core portions are contemplated to form the composite bioabsorbable materials of the present invention.

In general, the formation of a composite depends on both materials being heated to a temperature at which fusion of at least the surface of the materials begins. Where coextrusion is the method used to form the composite, both materials are heated to a temperature above their respective melting points. Where pressing is used to form the composites, the combination of temperature and pressure should be such that at least the surface of the core portion and the surface of the shell portion in contact therewith begin to fuse so that the two portions are joined into a unitary structure.

As will be appreciated by those skilled in the art, a certain amount of mixing of the core and shell materials will occur at the interface of those two portions. The amount of mixing may be only at the molecular level and thus, as a practical matter undetectable. However, in some instances the amount of mixing may be sufficient to produce a micro-shell layer at the interface between the shell and core portions. This micro-shell layer is made from a mixture of the core and shell materials and has its own bioabsorption profile.

The composite bioabsorbable materials of the present invention may be used to form various surgical devices. The composite filaments may be used as monofilament sutures or combined to make multifilament sutures. The filaments may be woven to form sheets which may be used to form various prosthetic devices such as vascular grafts, muscle grafts, bone fillers, etc. Alternatively the filaments can be formed into non-woven fabrics by lamination with or without additional polymeric matrix. Such non-woven fabrics may be used for the same purposes as the woven fabrics listed above.

The composite bioabsorbable sheets of the present invention may also be used to form prosthetic devices. Devices may be formed by molding the composite sheets into the above named devices. The sheets may also be formed into other surgical implants such as surgical clips, surgical fasteners, staples, bone pins, bone screws, anastomosis rings, wound dressings, drug delivery devices, etc.

It is within the scope of this invention to coat or impregnate the bioabsorbable composite materials of the present invention as well as implants and prosthetic devices made therefrom with one or more materials which enhance its functionality, e.g., surgically useful substances, such as those which accelerate or beneficially modify the healing process when the material is implanted within a living organism. Thus, for example, antimicrobial agents such as broad spectrum antibiotics (gentamicin sulphate, erythromycin or derivatized glyco-

peptides) which are slowly released into the tissue can be incorporated to aid in combating clinical and sub-clinical infections in a surgical or trauma wound site.

To promote wound repair and/or tissue growth one or several substances can be introduced into the composite bioabsorbable materials of the present invention or impregnated into fabrics or prostheses made from the composite bioabsorbable materials. Exemplary substances include polypeptides such as human growth factors. The term "human growth factor" or "HGF" embraces those materials, known in the literature, which are referred to as such and includes their biologically active, closely related derivatives. The HGFs can be derived from naturally occurring sources and are preferably produced by recombinant DNA techniques. Specifically, any of the HGFs which are mitogenically active and as such effective in stimulating, accelerating, potentiating or otherwise enhancing the wound healing process are useful herein. Growth factors contemplated for use in the materials of the present invention include hEGF (urogastrone), TGF-beta, IGF, PDGF, FGF, etc. These growth factors, methods by which they can be obtained and methods and compositions featuring their use to enhance wound healing are variously disclosed, *inter alia*, in U.S. Patent Nos. 3,883,497; 3,917,824; 3,948,875; 4,338,397; 4,418,691; 4,528,186, 4,621,052; 4,743,679 and 4,717,717; European Patent Applications 0 046 039; 0 128 733; 0 131 868; 0 136 490; 0 147 178; 0 150 572; 0 177 915 and 0 267 015; PCT International Applications WO 83/04030; WO 85/00369; WO 85/01284 and WO 86/02271 and UK Patent Applications GB 2 092 155 A; 2,162,851 A and GB 2 172 890 A, all of which are incorporated by reference herein. When incorporating wound healing substances such as those discussed above, it may be advantageous to use composite materials having at least one shell layer are formed from a bioabsorbable material having a relatively high rate of bioabsorption. By incorporating wound healing substances in a high rate bioabsorption layer, the substance will be more quickly absorbed while the remaining composite material will still retain sufficiently good mechanical properties to perform its medical or surgical function.

To decrease abrasion, increase lubricity, etc., the bioabsorbable composite materials can be coated with various substances. Copolymers of glycolide and lactide and polyethylene oxide, calcium salts such as calcium stearate, compounds of the pluronic class, copolymers of caprolactone, caprolactone with PEO, polyHEMA, etc. may be employed.

Table I below sets forth typical conditions for extruding, stretching composite monofilament sutures in accordance with this invention.

TABLE I

CONDITIONS OF MANUFACTURING COMPOSITE MONOFILAMENT OF THE PRESENT INVENTION		
	EXAMPLE	
Suture Size	3/0	
Material	Polycaprolactone	Polydioxanone
Process Conditions	Extrusion Operation	
Extruder	Extruder 1 (shell)	Extruder 2 (core)
extruder screw, rpm	0.6	1.3
pump rpm	4.4	5.8
barrel temp., °C, zone A	80	52
barrel temp., °C, zone B	120	135
barrel temp., °C, zone C	120	135
clamp temp., °C	120	135
adapter temp., °C	120	130
Process Conditions	Extrusion Operation	
pump temp., °C	120	135
barrel melt temp., °C	117	149
pump melt temp., °C	117	150
spinneret melt temp., °C	118	118
barrel pressure, psi	760	1250
pump pressure, psi	500	1000
spinneret pressure, psi	840	1980
pump size, cc per revolution	0.16	0.16
outside diameter of spinneret orifices, mm	0.28	--
inside diameter of spinneret orifices, mm	--	0.25
quench bath temp., °C	18	18

	Stretching (Orienting) Operation
	EXAMPLE
draw bath temp., °C	50
first godet, mpm	4.2
second godet, mpm	19.7
second oven temp., °C	70
third godet, mpm	24.6
draw ratio	5.9 : 1
	Annealing Operation
	EXAMPLE
oven temp., °C	50
time (hrs.)	18

The physical properties of the sutures and the procedures employed for their measurement are set forth in Table II as follows:

TABLE II

PROCEDURES FOR MEASURING PHYSICAL PROPERTIES OF COMPOSITE MONOFILAMENT SUTURES OF THE PRESENT INVENTION	
Physical Property	Test Procedure
knot-pull strength, kg	U.S.P. XXI, tensile strength, sutures (881)
straight-pull strength, kg	ASTM D-2256, Instron Corporation
elongation, %	ATSM D-2256
tensile strength, kg/mm ²	ASTM D-2256, Instron Corporation Series IX Automated Materials Testing System 1.03A

Table III below sets forth the physical properties of the composite monofilament suture of the present invention.

TABLE III

Physical Property	
diameter (mm)	0.295
shell thickness (mm)	0.036
core thickness (mm)	0.223
knot-pull strength (kg)	2.2
straight-pull strength (kg)	3.0
elongation (%)	26
tensile strength (kg/mm ²)	47

Although the composite bioabsorbable materials and processes for their manufacture have been described in terms of the preferred embodiments, numerous modifications will be readily apparent to those skilled in the art. For example, composite medical or surgical articles having a composite core/shell structure may be formed directly by coextrusion, injection molding, casting, etc. Composite materials having a core/shell structure may also be fabricated by lamination bonding techniques, e.g., hot isostatic pressing. Such techniques also result in composite materials whose mechanical properties may be described using the above rule of mixtures equation.

The claims which follow identify embodiments of the invention additional to those described in detail above.

Claims

1. A composite bioabsorbable filament implantable within a living organism comprising:
 - a core portion formed from a first bioabsorbable material;
 - a shell portion joined to said core portion, said shell portion formed from a second bioabsorbable material;
 - said first and second bioabsorbable materials having different rates of bioabsorption.
2. A bioabsorbable filament as recited in claim 1 wherein said first bioabsorbable material has a greater rate of bioabsorption than said second bioabsorbable material.
3. A bioabsorbable filament as recited in claim 1 wherein said second bioabsorbable material has a greater rate of bioabsorption than said first bioabsorbable material.
4. A bioabsorbable filament as recited in claim 1, 2 or 3 wherein said bioabsorbable filament is formed by coextruding said core portion and said shell portion.
5. A bioabsorbable filament as recited in any one of the preceding claims wherein said first bioabsorbable material comprises a glycolide-containing polymer and said second bioabsorbable material comprises polydioxanone.
6. A bioabsorbable filament as recited in any one of the preceding claims wherein said first bioabsorbable material comprises polydioxanone and said second bioabsorbable material comprises polycaprolactone.
7. A bioabsorbable filament as recited in any one of the preceding claims wherein said shell portion comprises a first shell portion formed from said second bioabsorbable material and a second shell portion formed from a third bioabsorbable material, said second and third bioabsorbable materials having different rates of bioabsorption.
8. A bioabsorbable filament as recited in any one of the preceding claims further comprising a coating formed over said shell portion.
9. A suture formed from the bioabsorbable filament of any one of the preceding claims.
10. A woven or non-woven prosthetic device made from the composite filament of claim 1.
11. A composite bioabsorbable sheet implantable within a living organism comprising:
 - a core portion formed from a first bioabsorbable material;
 - a shell portion joined to said core portion, said shell portion formed from a second bioabsorbable material;
 - said first and second bioabsorbable materials having different rates of bioabsorption.
12. A bioabsorbable sheet as recited in claim 11 wherein said first bioabsorbable material has a greater rate of bioabsorption than said second bioabsorbable material.
13. A bioabsorbable sheet as recited in claim 11 or 12 wherein said shell portion comprises a first shell portion formed from said second bioabsorbable material and a second shell portion formed from a third bioabsorbable material.

sorbable material, said second and third bioabsorbable materials having different rates of bioabsorption.

14. A method for making a composite bioabsorbable material comprising:

forming a first melt of a first bioabsorbable material;

5 forming a second melt of a second bioabsorbable material, said second bioabsorbable material having a different rate of bioabsorption than said first bioabsorbable material;

coextruding said first and second material melts to form a composite bioabsorbable material having a core portion and a shell portion integral with said core portion such that said first melt forms said core portion and said second melt forms said shell portion.

10

15. A method for making a composite bioabsorbable material as recited in claim 14 wherein said coextrusion is performed through a spinneret to form a filament, said filament then being stretched to form a monofilament suture.

15

20

25

30

35

40

45

50

55

FIG. 1A




FIG. 2A




FIG. 2B




FIG. 3




FIG. 4




FIG. 5



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 95 10 1228

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 6)
X	NL-A-9 201 035 (LOLKE JOHAN VAN DIJK) 3 January 1994 * the whole document *	1-3, 11, 12	A61L31/00 A61L17/00 A61L27/00 A61L15/26
Y	US-A-5 123 912 (KAPLAN DONALD S ET AL) 23 June 1992 * column 5, line 38 - line 50; claims *	1-15	
Y	EP-A-0 325 195 (ETHICON INC) 26 July 1989 * claims; example *	1-15	
A	WO-A-89 00431 (BIOCON OY) 26 January 1989 * page 6, line 3 - line 36; examples *	1-15	
A	EP-A-0 499 204 (UNITED STATES SURGICAL CORP) 19 August 1992 * claims; examples *	1-15	
A	FR-A-2 635 966 (ETHICON INC) 9 March 1990 * claims *	1-15	
A	EP-A-0 281 482 (RES TRIANGLE INST) 7 September 1988 * claims *	1	TECHNICAL FIELDS SEARCHED (Int. Cl. 6) A61L
A	US-A-4 047 533 (PERCIACCANTE VINCENT ANTHONY ET AL) 13 September 1977 * claims; examples *	1	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 6 June 1995	Examiner ESPINOSA, M
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 (02.92) (P0400)